

Athelie'



Ver. 1



Technical Data Sheet

Decorative finish with a contemporary antique effect

Walls are made to give us protection but this function is generally insufficient to satisfy our need of beauty, prestige and elegance. The Athelie' collection has been studied to allow you to select a finish with strong mysterious shadows and outstanding antique metallic effects to highlight modern and traditional interior architectures.



INTENDED USE

Any well treated, smooth, interior wall surface.



SURFACE TREATMENT

Ensure that the surface is clean, dry and sound. For new plasters or old and powdery walls, apply a coat of ADIFIX primer thinned as specified and allow to dry. Roller apply 1 or 2 basecoats of FONDO UNIVERSALE colored with 2/3 of Tinter DTX01 in 2lt. This basecoat color is the one to always use regardless of the tone selected for the finish.



COLOR

ATHELIE' can be applied after adding only the special Gold or Silver TINTER or it can be additionally colored by adding other tones of TINTER.



APPLICATION

Starting from the top corner downwards, apply the product in short, uneven crosshatched movements using the Sesiré Brush. Continue working for about 10 to 15 minutes (the exact time will depend on the temperature and humidity). At this point lightly trowel over the applied product with the Desiré Distender always in crossed movements using more or less pressure depending on how much you wish the colored flakes to show. Application B: Apply the product with a brush then with a stainless steel trowel in crosshatched movements with firm pressure, trowel down well to reach the typical effect of the product. It is also possible to apply the product directly the wall with the trowel using the same crossed movements, giving more or less pressure according to the effect you wish to reach. The samples shown on the catalogue are applied in 2 coats, the second applied in the same way after at least 6 hours from the first.



THINNING

Ready to use or with max. 5% water.



AVERAGE SPREAD RATE

application A: 8 to 9 m²/lt; application B: 6 to 7 m²/lt per coat



DRYING TIME AT 25° C

about 4 to 6 hours.



SPECIFIC GRAVITY

1040 ± 20 g/l



VISCOSITY

(Brookfield, 20° C): 10000 - 12000 mPa·s



ADVICES

Do not apply with air and surface temperatures below 5°C and above 28°C. All the products must be protected from freezing and well stored under cover. Carefully verify spread rates and the surface area to be coated to avoid running short of product during the working process and reducing the risk of differences in tones. Mix the products well before use. It is also advisable to mix together the product when using multiple cans for the same job and to use product and Tinters from the same production lots. Use fresh clean water for thinning and maintain the same thinning proportions throughout the same job. Remove masking tapes before drying of the products. Wash tools with warm water before the product dries. A correct surface preparation will guarantee a finer finished effect and better product yield. The drying times indicated may vary in relation to the air and surface temperature and the relative humidity. The spread rates of the products have only an indicative value and may vary notably according to the substrate condition and the skill of the applicator. The applicator should always make a test sample prior to carrying out the application.



PAKAGING

containers lt. 0.75x6 unit; lt. 3;



V.O.C. (Directive 2004/42/CE)

8 g/l; Cat. L BA (Max. Value 200 g/l)

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

