

Desiré



Ver. 1



Technical Data Sheet

Premium quality, white fleck, specialty wall finish

From the experience matured in many years of decorative paint production, adicolor proudly features DESIRÉ, the most widely used designer finish. a truly exquisite and unique fleck perfect interior for all functional and excellent for homes, offices, hotels, retail stores and all types of environments in either classical or contemporary style.



INTENDED USE

Any normal, paintable interior and exterior wall surface either Gypsum plaster based or rendered masonry.



SURFACE TREATMENT

Ensure that the surface is clean, dry and free from peeling paint or any substance that may compromise adhesion. In case of old and powdery walls or in presence of weak paint, apply a coat of ADIFIX primer thinned as specified and allow to dry. Roller or brush apply one or two basecoats of FONDO UNIVERSALE thinned with 20-30% water and let dry for 5-6 hours before applying the finish.



COLOR

Add the specified quantity of the chosen adicolor TINTER to the DESIRÉ White Base as indicated on the relative color chart and stir delicately until well blended.



APPLICATION

Use the special DESIRÉ brush and apply unevenly to the surface using short, crossed strokes, flipping and overlapping each time. Start applications from the top corner of the wall and work downwards, covering an area of approx. 3 to 5 sq.m at a time, according to the specific conditions. After about 10-15 minutes from application, when the product has just started to dry, lightly pass the Desiré Distender blade over the product in crossed movements to flatten the raised particles and reach the desired final effect.



THINNING

With 5 to 10% water



AVERAGE SPREAD RATE

Spread rate (per coat): 8 to 10 mq/litre



DRYING TIME AT 25° C

4 to 6 hours touch dry, 1 to 2 days, thoroughly dry



SPECIFIC GRAVITY

1040 ± 20 g/l



VISCOSITY

(Brookfield 20°C): 12000-15000 mPa.s



ADVICES

Do not apply with air and surface temperatures below 5°C or above 28°C. Carefully verify spread rates and the surface area to be coated to avoid running short of product during the working process and reducing the risk of differences in tones. It is also advisable to mix together the product when using different lots and multiple cans for the same job. Clean tools with warm water. Store the product well protected from freezing and excess heat.

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

