



Technical Data Sheet

Waterborne glazing top coat for interior or exterior use.

Ideal for high traffic areas to give a non-yellowing, mid-sheen, satin effect and extra protection de la gamme décorative Adicolor ou d'autres revêtements et peintures.



INTENDED USE

As a protective, glazing top coat, satin effect for interior and exterior.



SURFACE TREATMENT

Surfaces to treat must be perfectly dry and clean.



APPLICATION

Brush, roller or by spray.



THINNING

Ready to use.



AVERAGE SPREAD RATE

10 to 12 m²/litre



DRYING TIME AT 25° C

1 to 2 hours dust free, 2-3 hours touch dry. Recoatable after 12 hours.



SPECIFIC GRAVITY

1050 ± 20 g/l



VISCOSITY

(Brookfield, 20° C): 3000 - 4000 mPa·s



ADVICES

Do not apply with air and surface temperatures below 5°C and above 28°C. All the products must be protected from freezing and well stored under cover.

Carefully verify spread rates and the surface area to be coated to avoid running short of product during the working process.

Mix the products well before use. Wash tools with warm water before the product dries.

The drying times indicated may vary in relation to the air and surface temperature and the relative humidity. The spread rates of the products have only an indicative value and may vary notably according to the substrate condition and the skill of the applicator.



PAKAGING

containers lt. 1x6 unit; lt. 4;



V.O.C. (Directive 2004/42/CE)

20 g/l; Cat. L BA (Max. Value 200 g/l)

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

