



Ver. 1



Technical Data Sheet

Gold and silver base siloxane cream, patinated wax effect wall decoration

A superb siloxane cream in the enchanting silver and gold base version to easily and quickly achieve an impressively beautiful colored and free-form decoration enriched with a splendid luminous effect of delicate gold and silver reflects. It is ideal to give an elegant and rich creative finish with a warm glow that will bring life, depth and movement of color to any interior surface.



INTENDED USE

Any normal, paintable interior wall surface, either Gypsum plaster based or rendered masonry.



SURFACE TREATMENT

Ensure that the surface is clean, dry and sound. In case of old and powdery walls or in presence of weak paint, apply a coat of ADIFIX primer thinned as specified and allow to dry. Using a short-pile roller, apply one or two base coats of FONDO UNIVERSALE thinned with 20-30% water and let dry for min- 5-6 hours before applying the finish.



COLOR

To obtain the desired tone, add the specified quantity of Adicolor TINTER to the Velé GOLD or SILVER base as indicated on the relative color chart (or create new colors to your liking). Stir in delicately until well blended.



APPLICATION

Dip the widest part of the special Velé glove in the glaze without over saturating. Gently rest the glove on the wall and apply the product, working in circular and irregular movements. When necessary, re-dip the glove and resume the application at a distance of about 30-40 cm from where you left off, blending it in, to avoid excess overlapping. If a two color application of Velé is desired, the second coat can be applied once the previous color is completely dry. This optional second coat will improve the effect and produce a more intense tone. Velé Silver&Gold can also be applied by brush, sponge or other tool over various coatings to attain personalized cloudy, stained or fantasy effects to your liking.



THINNING

Ready to use



AVERAGE SPREAD RATE

Spread rate (per coat): 15 to 20 m²/litre



DRYING TIME AT 25° C

2 to 3 hours min.

Recoat time: 5 to 6 hours



SPECIFIC GRAVITY

1040 ± 20 g/l



VISCOSITY

(Brookfield 20°C): 5500 to 6500 mPa.s



V.O.C. (Directive 2004/42/CE)

Cat. L BA - Direttive 2004/42/CE - Val Max.: 200 g/l - Val Eff.: 95 g/l

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.